



Chamak Paintchem Limited

1471, MAHAVIRNAGAR, P.O. THAKKARNAGAR, NATIONAL HIGHWAY, AHMEDABAD-382 350.
(Gujarat) INDIA. ■ Ph. : 079-22703603, 22704607 ■ FAX : 079-22704815
Email : info@chamakpaint.com ■ URL : www.chamakpaint.com



CEMENT PRIMER (OIL BASE)

CHAMAK Cement Primer (Oil Base) solvent thinnable is used for priming plastered walls, bricks, asbestos, concrete to give good sealing properties. Its setting is fast. It has good resistance to water and wall alkalinity.

Recommended Use	: Plastered walls, bricks, asbestos, concrete etc. Suitable for interior use. For exterior purpose recommended subsequent coat must be applied over it.
Finish	: Smooth and matt.
Colour	: White
Covering Capacity on Smooth Surface	: 12 to 14 sq.mt./lit./coat for 15 micron dry film thickness depending upon surface & surface preparation by brushing.
Drying Time	: Surface Dry - Less than 30 minutes. Hard Dry - Less than 16 hours. Over coating time - 10 to 12 hours Minimum
Flash Point	: Above 30 ⁰ C (86 ⁰ F)
Thinner Recommended	: Synthetic G.P.Thinner
Application Viscosity	: Brushing - 40 to 50 sec at 30 ⁰ C by F.C. No :4 Brushing - 25 to 30 sec at 30 ⁰ C by F.C. No :4
Method of Application	: By brush or spray at a pressure of 40 to 50 P.S.I.
Subsequent Coat	: Synthetic Enamels, Under Coat's, Wall Finish
Direction For use	: Remove all loose flakes. Previous paint should be stripped off. Apply two coat's of primer by adjusting the viscosity with recommended thinner by brush. Allow prime coat to hard dry. Dry cut with sand paper before applying subsequent coats. stir well prior to use.
Packing	: 20 litres, 10 litres, 4 litres, 2 litres, 1 litres, & 500 mls.