



# Chamak Paintchem Limited

1471, MAHAVIRNAGAR, P.O. THAKKARNAGAR, NATIONAL HIGHWAY, AHMEDABAD-382 350.  
(Gujarat) INDIA. ■ Ph. : 079-22703603, 22704607 ■ FAX : 079-22704815  
Email : info@chamakpaint.com ■ URL : www.chamakpaint.com



## AUTOMOTIVE PAINT P. U. THINNER

This is specialised product from CHAMAK in two packs system of Base and hardener. It is formulated in accordance with the latest development in the lacquer industry. It is based on selected Grades of polyurethane, high grade of non oxidising resin. It is pigmented with high capacity, Light fast pigment to produce high gloss, hard durable film. It has very good Water, Petrol and Lubricating Oil resistance It has very good rubbing properties and durability.

Recommended Use	:	It is used for auto mobiles, two wheelers, transport vehicles and engineering goods, fans, refrigerators, machineries etc.
Finish	:	Smooth & Glossy
Colour	:	White, Black, Cream, Grey, Red etc.
Covering Capacity On Smooth Mild Stel Surface	:	10 To 12 Sp. Mt / Ltr, For 30 micron Dry Film Thickness.
Mixing Ration	:	Base To Hardner 3:1 by volume
Thinner Recommended	:	CHAMAK PU - Thinner.
Application Viscosity	:	For brushing - 25 to 30 sec. by FC-4 @ 30° C For spraying - 20 - 25 Sec. By FC-4 30° C
Curing Time	:	30 Minutes
Drying Time	:	SD approx 30 Minutes HD - approx 12-15 hours Recoating after 4 - 5 hours
Flash Point:	:	Above 25° C
Direction For Use	:	Remove dirt / grease / oil / dust. clean the surface properly. ensure that CHAMAK primer sufacer applied over the body has thoroughly dried and has been sanded down properly spray 2 to 3 coats. Now take out CHAMAK base and hardner mix them in 3:1 ratio 9by volume0 let the mixture stand for 30 minutes for cure. Now apply by brush or spray using recommended thinner use the mixture with in 4 hours.
Packing	:	20 Lit, 4 Lit, 1Lit.