



Chamak Paintchem Limited

1471, MAHAVIRNAGAR, P.O. THAKKARNAGAR, NATIONAL HIGHWAY, AHMEDABAD-382 350.
(Gujarat) INDIA. ■ Ph. : 079-22703603, 22704607 ■ FAX : 079-22704815
Email : info@chamakpaint.com ■ URL : www.chamakpaint.com



ZINC CHROME PRIMER TO IS 104

This is single pack airdrying, based on Syn. Resins and contains corrosion inhabiting pigments such as Zinc Chrome. it has very good anticorrosive property.

Recommended Use	: Protection of aluminium alloy/metal, structural steel, conveyors, storage tanks, etc.
Finish	: Smooth and matt to egg shell.
Colour	: Yellow
Covering Capacity on smooth Mild Steel Surface	: 10 to 11 sq. mt./lt. for 25 micron dry film thickness.
Drying Time	: Surface Dry - Less than 30 minutes. Hard Dry - Less than 16 hours.
Flash Point	: Above 30 ^o C (86 ^o F)
Thinner Recommended	: Synthetic G.P. Thinner
Method of Application	: By brush or spray at a pressure of 40 to 50 PSI.
Overcoat in Finish	: It can be overcoated with conventional product and Chlorinated Rubber Paint.
Direction For Use	: Ensure that surface should be free from rust, grease, oil, moisture and other loose flakes. Apply by brush or spray after adjusting to brushing or spraying viscosity by recommended thinner. Allow the primer coat to hard dry before applying finishing coat. Stir well before use. For galvanised steel and non. ferrous metals pretreat with wash Primer, followed by one coat of CHAMAK Zinc Chromate Primer.
Storage Life	: As long as containers are kept sealed, it can be stored up to twelve months without deterioration.
Packing	: 20 liters, 4 litre, 1 litre & 500 mis.